COAPUR™ 3020 BB

Bio-based and solvent free liquid polyurethane thickener

HEUR Polyurethane Thickener

TYPICAL CHARACTERISTICS

Water soluble non ionic polyurethane

Viscous whitish liquid Appearance

Solid Content (%) 20 Active Content (%) 20 7 Brookfield viscosity (mPa.s) 3000 Specific gravity 1.03 Solvent Water

DESCRIPTION

Coapur™ 3020 BB is a 90% bio-based HEUR thickener. Coapur™ 3020 BB is a solvent-free and APEO free pure associative polyurethane thickener (also called HEUR, NISAT or NSAT). It provides a pure Newtonian rheology to water-borne systems. It allow to adjust selectively high shear viscosities and thus ensures excellent film build, spatter resistance and leveling together with low dosage and flexibility of use.

RECOMMENDED ADDITION LEVEL

It typical dosage is between 0.5% and 3% (as delivered on total formulation weight). It should be added at levels between 0.5 and 1.5% depending on the rheological profile of the co-thickener, when used in combination, or between 1 and 3% when used as sole thickener.

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum

HANDLING & STORAGE

It should be protected from the effects of weathering and stored between 5 and 40°C and sheltered from direct sun expose. Once opened, packaging should be resealed immediately after use.

To be easily pumpable, Coapur™ 3020 BB should be used about 20°C. In these conditions, this product should be used within 12 months from delivery.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

Adhesives & Sealants

- Assembly
- Other Adhesives
- · Pressure Sensitive Adhesives

KEY BENEFITS

FORMULATION

- Color acceptance
- Easy handling
- Post addition

STORAGE

- Viscosity stability
- In-can appearence
- Syneresis resistance



••••

APPLICATION

- Film build
- Spatter resistance
- Brushability



FILM PROPERTIES

- Anticorrosion
- Levelling
- Rub out



 APEO free Yes Bacteria resistance Yes Heavy metal free Yes Solvent-free Yes

THICKENING MECHANISM

Associative

VISCOSITY CONTRIBUTION

High Shear contribution

PVC

PVC Low PVC Mid **PVC** High



2024-04-24



Page 1/