

Acrylic associative thickener for water-based systems

HASE Acrylic Thickener

Typical Characteristics

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	30
Active Content (%)	30
pH	3
Specific gravity	1.06
Solvent	Water

Description

Rheotech™ 4200 is an associative acrylic thickener designed to improve both the rheology and the color acceptance of water based formulations. Its outstanding effectiveness at medium shear rates allows to control very easily the perceived quality of paints during handling and to facilitate coating by roll or by bush, especially for finishing touches. Rheotech™ 4200 ensures safe additions of colorants in water based formulations, limiting viscosity changes and rub-out issues. Rheotech™ 4200 can be used in every kind of alkaline water based formulation and particularly in solvent and Alkyl Phenol Ethoxylate (APE) free formulations.

Standard Packaging

Other packaging may be available upon request

- 1000L IBC
- 200L Drum
- Bulk

Handling & Storage

It can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure. Once opened, packaging should be resealed immediately after use. Film-forming product, surface may dry in contact with air. A slight sedimentation can be visible at the bottom of drums or totes. This phenomenon is normal and has no impact on the use and level of performance as long as the solids content of the product meets the specification. If necessary, filter the product prior to its use. In these conditions, this product should be used within 6 months from delivery.

Health and environmental data

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

Adhesives & Sealants

- Assembly
- Other Adhesives
- Sealants

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

Key Benefits

Formulation

- Cost in use
- Color acceptance
- Compatibility

Storage

- In-can appearance
- Syneresis resistance
- Antisettling

Application

- Brushability
- Rollability
- Sag resistance

Film Properties

- Hiding power/Opacity
- Rub out
- Gloss

Thickening mechanism

Non Associative	●●●●○
Self Association	●●●●○
Associative	●●○○○

Viscosity contribution

Low Shear contribution	●●●●○
Mid Shear contribution	●●●●○
High Shear contribution	●●○○○

PVC

PVC Low	●●○○○
PVC Mid	●●○○○
PVC High	●●●●○