

CRAYVALLAC® LA-250

Liquid urea rheology modifier for post addition to low polarity solvent based coatings
Urea urethane

Typical Characteristics

Nature	Urea urethane
Appearance	Clear liquid
Solid Content (%)	45
Active Content (%)	45
Solvent	DMSO
Viscosity	300-700 (Viscosity (mPas) at 10000s-1 @25°C)
Color	7 max (Gardner)

Description

CRAYVALLAC® LA-250 is a modified urea dissolved in DMSO and is a pourable liquid rheology modifier for post addition to low polarity solvent based coatings. CRAYVALLAC® LA-250 should be added to the coating as a slow stream under low to medium shear conditions to ensure sufficient dispersion. Although efficient stirring is required to ensure homogeneity, elevated temperatures are not required for activation and the use of excessive shear should be avoided.

Recommended addition level

0.5-2.0% under low shear dispersion, post-addition.

Standard Packaging

Other packaging may be available upon request

- 200 Kg Drum
- 25 Kg Pail

Handling & Storage

It should be stored in the original containers in a dry place at temperatures between 20°C (68°F) and 30°C (86°F). Use corrosion-resistant storage tanks and piping. Avoid exposure to direct sunlight or frost.

Containers must be tightly closed after use to exclude moisture. The absorption of moisture will result in the premature crystallization of the modified urea. In these conditions, this product should be used within 12 months from delivery.

Processing instructions

CRAYVALLAC® LA-250 should be added to the coating as a slow stream under low to medium shear conditions to ensure sufficient dispersion. Although efficient stirring is required to ensure homogeneity, elevated temperatures are not required for activation and the use of excessive shear should be avoided.

Health and environmental data

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

Key Benefits

Formulation

- Easy handling
- Post addition
- Ready to use

Storage

- Antisettling
- In-can appearance
- Syneresis resistance

Application

- Brushability
- Rollability
- Temperature resistance

Film Properties

- Gloss
- Levelling
- Transparency

APEO free: Yes

Bacteria resistance: Yes

Thickening mechanism

Non Associative	●●●●●
Self Association	○●●●○
Associative	○●●○

Viscosity contribution

Low Shear contribution	●●●●●
Mid Shear contribution	●●●○
High Shear contribution	○●●○